

Coating

Glazed

Sizes

Specs

Standards / Value

FACE BRICK C216 FBX

Size

Avg. Comp. (PSI) 13,821

Avg. 24 Hr. Cold
Water Absor. 2.54Avg. 5 Hr. Boil
Absor. 3.22Avg. Saturation
Coeff. 0.79Avg. Initial Rate
Absor. 5.60

Test Report

 [Download](#)**Cleaning
Recommendation**

ProSoCo would recommend their **Vanatrol®** or **Safety Klean®** products. Diedrich recommends their **202V Vana-Stop™** or **910PM** products. EaCo Chem recommends their **NMD 80®**. Use per the cleanser manufacturer's instructions. Follow the recommendations in the Brick Industry Association's (BIA) **Technical Notes on Brick Construction 20**.