

Sizes

Specs

Standards / Value	FACE BRICK C216	FBX
Size		
Avg. Comp. (PSI)	19,536	
Avg. 24 Hr. Cold Water Absor.	2.71	
Avg. 5 Hr. Boil Absor.	4.27	
Avg. Saturation Coeff.	0.63	
Avg. Initial Rate Absor.	3.90	
Test Report	 Download	

Cleaning Recommendation

Belden Brick recommends using **Vanatrol®** to clean this product. Alternatively, **EaCo Chem NMD 80®** can be used to clean any of our brick.