

Coating

Sand

Sizes

Specs

Standards / Value

FACE BRICK C216 FBA

THIN BRICK C1088 TBA

Size

Thin

Avg. 24 Hr. Cold
Water Absor.

6.38

Avg. 5 Hr. Boil Absor.

10.47

Avg. Saturation
Coeff.

0.61

Test Report

 [Download](#)

Size

Avg. Comp. (PSI)

5,630

Avg. 24 Hr. Cold
Water Absor.

6.70

Avg. 5 Hr. Boil Absor.

11.80

Avg. Saturation
Coeff.

0.57

Avg. Initial Rate
Absor.

24.00