

Technical Data Sheet

Emporium Series
Hanley Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (μ /min per 30in ²)	Core Volume (%)
Brazilwood Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Brazilwood Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Brazilwood Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cream White Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cream White Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Cream White Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Dolomite Grey Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Dolomite Grey Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Dolomite Grey Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Golden Dawn Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Golden Dawn Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Golden Dawn Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Mink Grey Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Mink Grey Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Mink Grey Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Pearl River Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Pearl River Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Pearl River Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Sunset Flashed Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Sunset Flashed Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Sunset Flashed Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Sunset Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Sunset Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Sunset Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Tawny Beige Smooth		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Tawny Beige Smooth Ironspot		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25
Tawny Beige Wirecut		Modular	ASTM C216	SW	FBX	>10,000	<6	<10	<10	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED.